

COMPONENTS

HiTEC[®] 5704

Olefin Copolymer (OCP) Viscosity Index Improver



Shear Stable Liquid Viscosity Index Improver/Pour Point
Depressant for Crankcase Lubricants

HiTEC[®] 5704 Olefin Copolymer (OCP) Viscosity Index Improver

Shear Stable Liquid Viscosity Index Improver/Pour Point Depressant for Crankcase Lubricants

Key Performance Benefits

HiTEC[®] 5704 additive is a pour-depressed version of HiTEC[®] 5748 olefin copolymer (OCP) VI improver. HiTEC[®] 5704 additive is recommended for use in gasoline and diesel engine lubricants, particularly when excellent shear stability and high-temperature, high-shear-rate viscosity is desired.

HiTEC[®] 5704 additive exceeds the ACEA shear stability requirements, even in wide-span viscosity grades. Since HiTEC[®] 5704 additive is pour-depressed, treatment with supplemental pour point depressant may not be required.

Recommended Dosage

Dosages generally recommended to make the various multigrade viscosity crankcase oils are as follows:

SAE Grade	10W30	10W40	15W40	15W50	20W40	20W50
HiTEC [®] 5704 % wt.	6.0	10.0	8.0	11.0	4.0	7.0

Typical Characteristics

Appearance:	Hazy viscous liquid
Density at 15°C, g/ml:	0.870
Flash Point, °C (PMCC):	155 min.
Kinematic Viscosity at 100°C, mm ² /s:	1100
Thickening Power at 100°C, mm ² /s: ⁽¹⁾	6.55
Shear Stability Index: ⁽¹⁾	22

Handling Information

Max Short Term Handling Temp: 120 °C
Shelf Life: 36 months at ambient temperature

(1) 11.5% wt. HiTEC[®] 5704 additive in SN oil (5.2 mm²/s at 100°C)

© 2011. Afton Chemical Corporation is a wholly-owned subsidiary of NewMarket Corporation (NYSE:NEU). HiTEC[®] is a trademark of Afton Chemical Corporation. 07/11.

The information in this bulletin is, to our best knowledge, sure and accurate, but all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control. Afton Chemical Corporation and its affiliates disclaim any liability incurred in connection with the use of these data or suggestions. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.